

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 827 137 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

04.03.1998 Bulletin 1998/10(51) Int. Cl.⁶: **G11B 5/704, G11B 5/706**(21) Application number: **97114597.4**(22) Date of filing: **22.08.1997**

(84) Designated Contracting States:

**AT BE CH DE DK ES FI FR GB GR IE IT LI LU MC
NL PT SE**(30) Priority: **27.08.1996 JP 242544/96**(71) Applicant: **Dowa Mining Co., Ltd.
Tokyo 100 (JP)**

(72) Inventors:

- Hisano, Seichi
Chiba-shi, Chiba-ken, 262 (JP)
- Salto, Kazuhisa
Okayama-shi, Okayama-ken, 700 (JP)

• Sano, Kazushi

Okayama-shi, Okayama-ken, 702 (JP)

• Konno, Shinichi

Okayama-shi, Okayama-ken, 702 (JP)

• Horikawa, Yoshichika

Okayama-shi, Okayama-ken, 702 (JP)

• Aihara, Yasuhiko

Okayama-shi, Okayama-ken, 702 (JP)

(74) Representative:

Geyer, Ulrich F., Dr. Dipl.-Phys. et al
WAGNER & GEYER,
Patentanwälte,
Gewürzmühlstrasse 5
80538 München (DE)

(54) **Coating type magnetic recording medium having a multilayer structure**

(57) A coating type magnetic recording medium having a multi layer structure exhibits excellent strength, surface smoothness, and weather resistance is formed on a substrate, and comprises a magnetic layer of magnetic particles dispersed in a resinous binder, and a non-magnetic layer of non-magnetic particles dispersed in a resinous binder. The magnetic particles are composed of acicular ferromagnetic metal particles of Fe containing Co, Al, rare earth elements, periodic table group 1a and 2a elements. The non-magnetic particles are composed of acicular particles of α -FeOOH.

EP 0 827 137 A1

Description

BACKGROUND OF THE INVENTION

5 Field of the Invention

The present invention relates to a coating type magnetic recording medium having a multilayer structure.

Description of the Prior Art

10

In a coating-type magnetic recording medium composed of a magnetic layer formed on a substrate by coating the substrate with a coating film of magnetic particles dispersed in a binder resin, it is desirable for the magnetic layer to have a smaller thickness to obtain low-noise, high-output characteristics. To accomplish this, coating type magnetic recording media having a multilayer structure have been proposed comprising forming between the magnetic layer and the substrate a non-magnetic coating layer obtained by dispersing non-magnetic particles in a binder resin. In this specification, the non-magnetic layer is also referred to as "lower layer" and the magnetic layer as "upper layer."

As the non-magnetic particles used to form the lower layer, there are mainly used spherical particles of titanium oxide or acicular particles of iron oxide. This type of multilayer magnetic recording medium is described in, for example, Japanese Patent Application Laid-Open (KOKAI) No. 63-187418 (1988), Japanese Patent Application Laid-Open (KOKAI) No. 4-167225 (1992) Japanese Patent Application Laid-Open (KOKAI) No. 6-60362 (1994) and Japanese Patent Application Laid-Open (KOKAI) No. 6-131653 (1994). It is also proposed in Japanese Patent Application Laid-Open (KOKAI) No. 4-167225 (1992), Japanese Patent Application Laid-Open (KOKAI) No. 6-139553 (1994), Japanese Patent Application Laid-Open (KOKAI) No. 6-215360 (1994), Japanese Patent Application Laid-Open (KOKAI) No. 7-78331 (1995), Japanese Patent Application Laid-Open (KOKAI) No. 7-105530 (1995), Japanese Patent Application Laid-Open (KOKAI) No. 7-182649 (1995), Japanese Patent Application Laid-Open (KOKAI) No. 7-282443 (1995), Japanese Patent Application Laid-Open (KOKAI) No. 7-326037 (1995) and Japanese Patent Application Laid-Open (KOKAI) No. 7-334835 (1995), among others. These describe characteristic values obtained when acicular hematite and the like are employed as the non-magnetic particles of the lower layer. That iron oxide hydrate and the like can be used for the lower layer is also stated, but characteristic values thereof are not included.

With respect to a magnetic recording medium having a multilayer structure, there is no actual record of FeOOH particles being used for the lower layer, neither do the above publications describe any specific examples or properties relating to when FeOOH particles are used for the lower layer. As such, there are many unknowns concerning which iron oxide hydrate will exhibit the intended functions when used as the particles of the lower layer of a magnetic recording medium. FeOOH is usually produced by oxidizing a suspension of Fe(OH)₂, but it is well known that even slight variation in oxidising conditions can result in different phases, and differences in properties and morphology. Clearly, therefore, not all known iron oxide hydrates have the right properties for use as lower layer particles.

The magnetic upper layer of a magnetic recording medium having a multilayer structure is required to be as thin as possible and to have a high density. This means that the magnetic particles have to be finer and have superior magnetic properties, and have excellent dispersibility so as not to degrade the resinous binder. When suitably combined with the lower layer, it is also required for the product medium to have excellent strength, storage-stability and weather resistance, and excellent surface smoothness, while retaining the excellent magnetic qualities.

For applying FeOOH to form the particles used in the lower layer to obtain a magnetic recording medium having a multi layer structure that exhibits excellent magnetic properties, surface qualities, strength, weather resistance and so forth, in accordance with the present invention, it was necessary to clarify what effect the chemical and physical properties and shape of the particles would have on the surface smoothness, strength, magnetic properties, and weather resistance of the magnetic recording medium, and what were the most suitable magnetic particles for the upper layer that is combined with the lower layer.

SUMMARY OF THE INVENTION

50

According to the present invention is provided a coating type magnetic recording medium having a multilayer structure, formed on a substrate, comprising a magnetic layer of magnetic particles dispersed in a resinous binder, and a non-magnetic layer of non-magnetic particles dispersed in a resinous binder, said magnetic particles being composed of acicular ferromagnetic metal particles of Fe containing from more than 5 to 50 at.% Co, 0.1 to 30 at.% Al, 0.1 to 10 at.% rare earth elements (including Y), up to 0.05 wt.% periodic table group 1a elements and up to 0.1 wt.% (including 0 wt.%) periodic table group 2a elements, said non-magnetic particles being composed of acicular particles of α -FeOOH having an average major axis diameter of 0.01 to 0.5 μ m and releasing not more than 2 wt.% of H₂O at 100°C.

The above and other features of the invention will be better understood from the following description made with

respect to the drawings.

BRIEF DESCRIPTION OF THE DRAWINGS:

5 Figure 1 is an electron microphotograph showing the shapes (branching) of the individual acicular particles of α -FeOOH of the lower layer, in accordance with the present invention.

Figure 2 is a graph showing the relationship between the Al content and the decomposition temperature of the α -FeOOH.

10 DETAILED DESCRIPTION OF THE INVENTION

The aim of providing a non-magnetic lower layer of a dispersion of non-magnetic particles between the substrate and the magnetic layer is to reduce the thickness of the magnetic layer while ensuring output in short-wavelength recording regions, and to obtain improved electromagnetic conversion characteristics such as erase and overwrite characteristics. To achieve this, the magnetic layer itself has to have the requisite properties. These requirements are satisfied by the magnetic particles according to the present invention. Before describing these magnetic particles, the lower layer particles that enable these properties to be obtained will be described.

15 First, with respect to the non-magnetic particles used for the lower layer, the role of the non-magnetic lower layer in the coating type magnetic recording medium having a multilayer structure includes being able to be coated on the thin magnetic layer with a smooth surface having few non-uniformities, that is, the non-magnetic layer itself has to have good surface smoothness, imparting strength to the magnetic recording medium, and adequately bringing out the magnetic properties of the magnetic upper layer.

20 When granular particles of titanium oxide that have been used as lower layer particles were formed into a tape, the strength thereof was insufficient compared to acicular particles, and it was difficult to make the particles finer. In the case of acicular hematite, with the production method used it is impossible to prevent sintering of the particles, so that sufficient surface smoothness cannot be obtained.

25 When forming a coating film of α -FeOOH dispersed in a resinous binder, depending on the binder, the chemical and physical qualities as well as the dimensions and shape of the α -FeOOH particles can have a major bearing on surface smoothness, strength and other such properties. It was found that acicular α -FeOOH particles that have an average major axis diameter of 0.01 to 0.5 μm and release not more than 2 wt.% of H_2O at 100 °C can be used to form a lower layer having the required surface smoothness and strength, and improve the qualities of the magnetic layer.

30 Moreover, the lower layer can perform the required functions more advantageously when the α -FeOOH particles are acicular particles with branches inclined in a two-dimensional direction and an average major axis diameter of 0.01 to 0.5 μm ,

35 and release not more than 2 wt.% of H_2O at 100°C. The above functions can be performed more advantageously when the α -FeOOH particles are acicular particles that contain 0.1 to 30 percent by weight Al, have an average major axis diameter of 0.01 to 0.5 μm , and release not more than 2 wt.% of H_2O at 100°C.

40 The above functions can also be performed more advantageously when the α -FeOOH particles are acicular particles that contain 0.1 to 30 percent by weight Si, have an average major axis diameter of 0.01 to 0.5 μm and release not more than 2 wt.% of H_2O at 100°C.

The above functions can also be performed more advantageously when the α -FeOOH particles are acicular particles that contain a combined total of 0.1 to 30 percent by weight of Al and Si, have an average major axis diameter of 0.01 to 0.5 μm and release not more than 2 wt.% of H_2O at 100 °C.

45 The above functions can also be performed more advantageously when the α -FeOOH particles are acicular particles having an average major axis diameter of 0.01 to 0.5 μm , a TAP density of 0.4 or more and release not more than 2 wt.% of H_2O at 100°C.

50 The above functions can also be performed more advantageously when the α -FeOOH particles are acicular particles that have an average major axis diameter of 0.01 to 0.5 μm , contain 0.1 to 30 percent by weight Al, have an atmospheric decomposition temperature of 210°C or higher, preferably 215°C or higher, and release not more than 2 wt.% of H_2O at 100°C.

In addition to the above properties, it is also desirable for the α -FeOOH particles of the present invention to have the following properties.

55 A BET specific surface area that is within the range 10 to 300 m^2/g , preferably 40 m^2/g or more, and more preferably 40 to 150 m^2/g ; a TAP density of 0.3 to 0.8 g/cm^3 , preferably 0.40 g/cm^3 or more; a compression density of 0.5 to 3.0 g/cm^3 , preferably 1.0 to 2.0 g/cm^3 ; and a true specific gravity of 3.0 to 6.0 g/cm^3 , preferably 3.5 to 4.3 g/cm^3 . The high TAP density and compression density relative to the true specific gravity facilitates compression of the particles in the coating film during the calendaring step of the tape formation process, which has the effect of improving the surface smoothness of the tape. A crystalline diameter of 10 to 200 angstrom, preferably 50 to 150 angstrom.

Thus, it is desirable that, in size, the α -FeOOH particles have an average major axis diameter of 0.01 to 0.5 μm , an average minor axis diameter of 0.01 to 0.05 μm , an average aspect ratio of 1 to 30, a specific surface area of 10 to 300 m^2/g , and a crystalline diameter of 10 to 200 angstrom. The fineness of these particles, especially their small minor axis diameter, results in a smoother tape surface, while the crystalline diameter and specific surface area reflects the major axis diameter.

The surface treatment condition and pH of the α -FeOOH particles also have an influence on the dispersibility when forming the coating material, and therefore also affect the surface smoothness. Favorable ranges for these are as follows; it is desirable to adjust the values to within these ranges.

Amount of stearic acid adsorption: 0.1 to 3.0 mg/m^2 .

Amount of resin adsorption: 0.5 to 4.0 mg/m^2 .

pH: A particle pH of 6 to 11, preferably 8 to 10, more preferably 8.0 to 9.5. Adjusting to this pH improves dispersibility when forming the coating material, and serves to improve the surface smoothness.

The particles for the lower layer according to this invention can be obtained by the method generally used to produce α -FeOOH. One such process comprises, for example, producing the particles by oxidizing a suspension containing colloidal ferrous hydroxide particles and having a pH of not less than 11, which is obtained by adding not less than an equivalent of an alkali hydroxide solution to an aqueous salt solution, by passing an oxygen-containing gas thereinto at a temperature not higher than 80°C, followed by drying and moisture-conditioning, while another such process comprises producing the particles by oxidizing a suspension obtained by reacting an aqueous ferrous salt solution with an aqueous alkali carbonate solution, by passing an oxygen-containing gas thereinto, followed by drying and moisture-conditioning. Unlike in the production of hematite particles, α -FeOOH particles obtained by such a method are not subjected to a high-temperature treatment step, so a problem of particles sintering together does not arise.

Figure 1 is a transmission electron microphotograph of α -FeOOH particles according to the present invention, with a major axis diameter of 0.30 μm , Al content of 2.8 wt.%, and a specific surface area (BET) of 65 m^2/g . As revealed by Figure 1, the particles have branches with an inclination parallel to the drawing sheet. This can be seen from the fact that even when a particle has three or more branches, the angles of the branches appear substantially uniform. If most of the components were normal to the plane of the drawing sheet, the branching angles would have appeared to be sharper. The fact that even with respect to particles that have a plurality of branches each of the branches is inclined in a two-dimensional direction in a specific plane, contributes to the surface smoothness of a lower layer in which the particles are used. This is because when the coating is applied, there are few branch components perpendicular to the substrate plane. Mutual twining of the branches also serves to improve the strength of the tape.

An especially smooth surface is obtained when the particles dispersed in the resin binder coated on the substrate have a major axis diameter of not more than 0.5 μm . As can also be seen in Figure 1, the fine acicular α -FeOOH particles are characterized by having a high aspect ratio resulting from the very fine minor axis diameter, resulting during the coating in good orientation in the longitudinal direction of the tape (the branches also being oriented in this direction), improving the strength of the tape as well as the surface smoothness.

Providing the α -FeOOH with a suitable Al content improves the heat resistance and storage-stability. With an Al content of 0.1 to 30 wt.%, the α -FeOOH particles can be stably maintained without undergoing change even when the temperature is being lowered during the drying step of tape formation. The effect provided by the Al is insufficient when the Al content is less than 0.1 wt.%. An Al content that exceeds 30 wt.% increases the specific surface area of the particles, degrading the dispersibility. With respect to when Al is contained as a compound, the Al content as used herein refers not to the content of the compound but to the content of just the element Al. The Al content may be Al occluded within the α -FeOOH or Al cladding on the surface.

The Al may be contained in the α -FeOOH in the form of a water-soluble salt such as $\text{Al}_2(\text{SO}_4)_3$, $\text{Al}(\text{NO}_3)_3$ and AlCl_3 , or a water-soluble aluminate compound such as NaAlO_2 (sodium aluminate). An Al compound can be used to clad the surface of the α -FeOOH with Al by, for example, dissolving the Al compound in an alkaline solution, dispersing the α -FeOOH in the solution, neutralizing the solution by blowing carbonic gas into the solution or by adding an acid, thereby cladding the surface of the particles with Al in the form of crystalline or amorphous $\text{Al}_2\text{O}_3 \cdot n\text{H}_2\text{O}$ (aluminum hydroxide). The Al can be occluded within the α -FeOOH particles by adding the water-soluble Al salt or aluminate to the reaction system used to produce α -FeOOH and the like by using a neutralizer such as NaOH , Na_2CO_3 , or NH_4OH to neutralize a ferrous salt solution such as a solution of FeSO_4 or FeCl_2 and then oxidizing the solution in air, for example.

The surface quality of the particles according to the present invention may also be controlled by using other elements such as a Si compound. The content range in the case of Si is 0.1 to 30 wt.%. When Al and Si are both used, the combined total content should be within the range 0.1 to 30 wt.%. With respect to when Si is contained as a compound, the Si content as used herein refers not to the content of the compound but to the content of just the element Si.

It was found that the temperature at which the α -FeOOH when heated would decompose in air varied depending on the Al content of the α -FeOOH. Figure 2 shows the relationship between the temperature at which decomposition

began and ended plotted and the Al content (wt.%) of the α -FeOOH. The decomposition temperatures were measured using a differential thermal analyzer that complies with JIS K7120. The curves that join the stars in Figure 2 were deduced from plots of measured values. It can be seen from these curves that the temperatures at which α -FeOOH decomposition starts and ends rise with the increase in the Al content. Typical values of the curves are shown in the following table.

Al content of α -FeOOH (wt.%)	Decomposition starting temperature	Decomposition ending temperature
0	190 °C	250 °C
1	220	290
5	250	330
10	270	350

The properties of the lower layer are affected by the moisture amount of the α -FeOOH. The amount of moisture released when the α -FeOOH is maintained at 100°C must not exceed 2 wt.%, and preferably does not exceed 1.5 wt.%. If the amount of moisture released at 100°C is more than 2 wt.%, the dispersibility in the binder resin will be insufficient, and even if coating is effected, implementing a tape is difficult. This moisture amount can be measured using the moisture measurement principle according to the Carl Fischer method. An example is shown below.

Al content of α -FeOOH particles (wt.%)	Major axis diameter of α -FeOOH particles (μ m)	Amount of moisture released (wt.%)	
		100°C	160°C
2.8	0.30	1.09	1.84
4.3	0.15	0.76	1.45

Specific effects resulting from the use of α -FeOOH for the particles of the lower layer of the magnetic recording medium having a multilayer structure according to the present invention will now be shown, with reference to test examples.

We begin by describing the methods used to measure the values of properties shown in the test examples. The same measurement methods are also used for the examples described later. The average major axis diameter (denoted by l in the tables), average minor axis diameter (denoted by d), and aspect ratio (l/d) are average values obtained from measuring 100 particles in electron microphotographs that show the particles magnified 108,000 times in the case of lower layer particles, and 174,000 times in the case of upper layer magnetic metal particles. The crystalline diameter (denoted by D_x) was calculated by obtaining the peak half width corresponding to the (110) plane from a profile obtained with an x-ray diffraction apparatus, and substituting this into a Scherrer formula.

The specific surface area (denoted by BET) was measured using the BET method. The stearic acid adsorption amount (denoted by STA or St. adsorption amount) was calculated as the adsorption amount per specific surface area obtained by dispersing sample particles in a 2% MEK solution of stearic acid, centrifuging the solution to cause the particles to settle and measuring the concentration of the clear upper layer. The amount of resin adsorption (denoted by Resin) was calculated by the same method, using a 2% MIBK solution of polyurethane resin.

The pH was measured according to JIS K5101. The true specific gravity was measured by the immersion method, using toluene as the solvent. The compression density (denoted by CD) is the density of the sample compressed at a pressure of 80 kgf/cm². The TAP density (denoted by TAP) was measured according to JIS K5101. Particle moisture related measurements were based on changes in weight at 100°C (or 300°C) in accordance with the Carl Fischer method. Decomposition starting and ending temperatures were obtained from thermal differential data. Moisture amount based changes in viscosity were obtained when the particles were dispersed in the coating material by using an E type viscometer to measure the viscosity of the coating material. The surface smoothness was evaluated based on the surface roughness R_a of the base layer surface of the tape, as measured using a three-dimensional fine shape measuring machine (model ET-30HK) manufactured by Kabushiki Kaisha Kosaka Laboratory.

Also in the tables,

H_c is coercive force (Oe);

σ_s is saturation magnetic flux density of magnetic metal particles (emu/g);

σ_r is residual magnetic flux density of magnetic metal particles (emu/g);

Br is residual magnetic flux density of tape (gauss);

B_m is saturation magnetic flux density of tape (gauss);

σ_r/σ_s and Br/B_m are remanence ratios;

Δσ_s and ΔB_m are the ratios of decrease (%) in σ_s and B_m after one week in an atmosphere at 60°C and a relative humidity (RH) of 90%.

The presence or absence of precipitates following weather resistance tests refers to whether or not precipitates are observed on the tape surface after one week in an atmosphere at 60°C and a relative humidity (RH) of 90%, said observation being by means of a microscope. A Hi-8 video deck was used to measure the electromagnetic conversion characteristics.

Lower layer particle test examples

Lower layer example 1

Coating material having the following composition was prepared.

α-FeOOH	100 parts by weight
(In this example, the major axis diameter was 0.15 μm and moisture amount at 100°C was 1 wt.%.)	
Polyurethane resin	20 parts by weight
Methyl ethyl ketone	165 parts by weight
Cyclohexanon	65 parts by weight
Toluene	165 parts by weight
Stearic acid	1 part by weight
Acetyl acetone	1 part by weight

Coating material having the above composition obtained after dispersion for one hour using a centrifugal ball mill was applied with an applicator to a polyethylene terephthalate base film to a target thickness of approximately 3 μm to form a non-magnetic lower layer. The properties of the α-FeOOH used and of the lower layer thus obtained are listed in Table 1-A and Table 1-B (these values of the following examples and comparative examples are also listed in Table 1-A and 1-B).

Lower layer example 2

A lower layer was produced in the same way as in example 1 except that instead of the α-FeOOH particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, α-FeOOH particles were used having a major axis diameter of 0.15 μm and 0.2 wt.% Al cladding.

Lower layer example 3

A lower layer was produced in the same way as in example 1 except that instead of the α-FeOOH particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, α-FeOOH particles were used having a major axis diameter of 0.15 μm and 0.1 wt.% Al cladding.

Lower layer example 4

A lower layer was produced in the same way as in example 1 except that instead of the α-FeOOH particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, α-FeOOH particles were used having

a major axis diameter of 0.15 μm and 2.5 wt.% Al cladding.

Lower layer example 5

- 5 A lower layer was produced in the same way as in example 1 except that instead of the α -FeOOH particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, α -FeOOH particles were used having a major axis diameter of 0.15 μm and 5.0 wt.% Al cladding.

Lower layer example 6

- 10 A lower layer was produced in the same way as in example 1 except that instead of the α -FeOOH particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, α -FeOOH particles were used having a major axis diameter of 0.15 μm and 30.0 wt.% Al cladding.

15 Lower layer example 7

A lower layer was produced in the same way as in example 1 except that instead of the α -FeOOH particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, α -FeOOH particles were used having a major axis diameter of 0.15 μm and 1.0 wt.% occluded Al.

20 Lower layer example 8

- A lower layer was produced in the same way as in example 1 except that instead of the α -FeOOH particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, α -FeOOH particles were used having a major axis diameter of 0.15 μm and 2.5 wt.% occluded Al.

Lower layer example 9

- 30 A lower layer was produced in the same way as in example 1 except that instead of the α -FeOOH particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, α -FeOOH particles were used having a major axis diameter of 0.15 μm and 5.0 wt.% occluded Al.

Lower layer example 10

- 35 A lower layer was produced in the same way as in example 1 except that instead of the α -FeOOH particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, α -FeOOH particles were used having a major axis diameter of 0.15 μm and 10.0 wt.% occluded Al.

Lower layer example 11

- 40 A lower layer was produced in the same way as in example 1 except that instead of the α -FeOOH particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, α -FeOOH particles were used having a major axis diameter of 0.15 μm and 20.0 wt.% occluded Al.

45 Lower layer example 12

A lower layer was produced in the same way as in example 1 except that instead of the α -FeOOH particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, α -FeOOH particles were used having a major axis diameter of 0.10 μm .

50 Lower layer example 13

- A lower layer was produced in the same way as in example 1 except that instead of the α -FeOOH particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, α -FeOOH particles were used having a major axis diameter of 0.30 μm .

Lower layer example 14

5 A lower layer was produced in the same way as in example 1 except that instead of the α -FeOOH particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, α -FeOOH particles were used having a major axis diameter of 0.05 μm and 5.0 wt.% Al cladding.

Lower layer example 15

10 A lower layer was produced in the same way as in example 1 except that instead of the α -FeOOH particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, α -FeOOH particles were used having a major axis diameter of 0.10 μm and 5.0 wt.% Al cladding.

Lower layer example 16

15 A lower layer was produced in the same way as in example 1 except that instead of the α -FeOOH particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, α -FeOOH particles were used having a major axis diameter of 0.30 μm and 5.0 wt.% Al cladding.

Lower layer example 17

20 A lower layer was produced in the same way as in example 1 except that instead of the α -FeOOH particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, α -FeOOH particles were used having a major axis diameter of 0.05 μm and 5.0 wt.% occluded Al.

25 Lower layer example 18

30 A lower layer was produced in the same way as in example 1 except that instead of the α -FeOOH particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, α -FeOOH particles were used having a major axis diameter of 0.10 μm and 5.0 wt.% occluded Al.

Lower layer example 19

35 Lower layers were produced in which instead of the α -FeOOH particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, α -FeOOH particles were used having a major axis diameter of 0.30 μm , 5.0 wt.% occluded Al, and a moisture amount of (A) 0.5 wt.%, (B) 1.0 wt.%, and (C) 2.0 wt.%.

Lower layer example 20

40 A lower layer was produced in the same way as in example 1 except that instead of the α -FeOOH particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, α -FeOOH particles were used having a major axis diameter of 0.50 μm and 5.0 wt.% occluded Al.

Lower layer comparative example 1

45 A lower layer was produced in substantially the same way as in example 1 except that instead of the α -FeOOH particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, α -Fe₂O₃ particles were used having a major axis diameter of 0.15 μm .

Lower layer comparative example 2

50 A lower layer was produced in substantially the same way as in example 1 except that instead of the α -FeOOH particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, titanium oxide particles were used having an average diameter of 0.035 μm .

55 Lower layer comparative example 3

A lower layer was produced in the same way as in example 1 except that instead of the α -FeOOH particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, α -FeOOH particles were used having

a major axis diameter of 0.15 μm and 35.0 wt.% Al cladding.

Lower layer comparative example 4

5 A lower layer was produced in the same way as in example 1 except that instead of the $\alpha\text{-FeOOH}$ particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, $\alpha\text{-FeOOH}$ particles were used having a major axis diameter of 0.15 μm and 35.0 wt.% occluded Al.

Lower layer comparative example 5

10 A lower layer was produced in the same way as in example 1 except that instead of the $\alpha\text{-FeOOH}$ particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, $\alpha\text{-FeOOH}$ particles were used having a major axis diameter of 0.005 μm .

15 Lower layer comparative example 6

A lower layer was produced in the same way as in example 1 except that instead of the $\alpha\text{-FeOOH}$ particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, $\alpha\text{-FeOOH}$ particles were used having a major axis diameter of 0.60 μm .

20 Lower layer comparative example 7

A lower layer was produced in the same way as in example 1 except that instead of the $\alpha\text{-FeOOH}$ particles having a major axis diameter of 0.15 μm used to form the coating material of example 1, $\alpha\text{-FeOOH}$ particles were used having
25 a major axis diameter of 0.60 μm and 5.0 wt.% Al cladding.

Lower layer comparative example 8

A lower layer was produced in the same way as in example 1 except that instead of the $\alpha\text{-FeOOH}$ particles having
30 a major axis diameter of 0.15 μm used to form the coating material of example 1, $\alpha\text{-FeOOH}$ particles were used having a major axis diameter of 0.60 μm and 5.0 wt.% occluded Al.

35

40

45

50

55

Table 1 - (A)

Lower layer Example No.	Parti- cle material	Al content wt%	Form of Al content	Moist- ure c- ontant wt%	Decompo- sition starting tempera- ture °C	Decompo- sition ending tempera- ture °C	Major axis diameter μm	Minor axis diameter μm	I/d	BET m ² /g	D x A	ST A mg/m ²	Resin mg/m ²	PH	True sp- ecific gravity g/cm ³	CD g/cm ³	T A P g/cm ³	Visco- sity (p)	Roug- hness A	Stran- gth mg
Lower layer Ex. 1	FeOOH	0		1	190	250	0.15	0.022	6.8	101	80	1.18	1.08	9	4.08	1.23	0.52		135	95
Compara- tive Ex.	1 Fe ₂ O ₃			1			0.15	0.025	6.0	55	170	1.61	1.61	9	5.07	1.85	0.65		154	90
	2 TiO ₂						0.035			40				7	4.10				145	80
Lower layer Example	2 FeOOH	0.2		1			0.15	0.022	6.8	100	80	1.15	1.05	9	4.08	1.23	0.52		135	95
	3 FeOOH	1		1			0.15	0.022	6.8	96	80	1.18	1.08	9	4.08	1.24	0.5		125	98
	4 FeOOH	2.5		1			0.15	0.022	6.8	90	80	1.20	1.09	9	4.08	1.25	0.49		120	100
	5 FeOOH	5		1			0.15	0.022	6.8	84	80	1.22	1.12	9	4.08	1.26	0.48		115	105
	6 FeOOH	30		1			0.15	0.022	6.8	100	80	1.25	1.15	9	4.08	1.26	0.47		125	100
	Comparative Example 3	FeOOH	35	1			0.15	0.022	6.8	110	80	0.32	0.35	9	4.08	1.24	0.46		180	80
Lower layer Example	Cladding																			
	7 FeOOH	1		1	220	290	0.15	0.023	6.5	100	81	1.15	1.05	9	4.05	1.25	0.48		108	100
	8 FeOOH	2.5		1			0.15	0.024	6.3	108	82	1.10	1.01	9	4.02	1.26	0.47		105	102
	9 FeOOH	5		1	250	330	0.15	0.025	6.0	118	83	1.04	0.94	9	4.00	1.27	0.46		100	107
	10 FeOOH	10		1	270	350	0.15	0.027	5.6	135	84	1.00	0.9	9	3.95	1.28	0.45		110	105
Comparative Example 4	11 FeOOH	20		1			0.15	0.030	5.0	147	85	0.99	0.89	9	3.90	1.29	0.44		120	104
	FeOOH	35	Occluded	1			0.15	0.032	4.7	350	87	0.51	0.41	9	3.85	1.27	0.45		155	82

Table 1-(B)

Lower layer Example No.	Particle material	Al content wt%	Form of Al content	Moist- ure c- ontent wt %	Decompo- sition starting tempera- ture °C	Decompo- sition ending tempera- ture °C	Major axis diameter μm	Minor axis diameter μm	I/d	BET d/g	D x A	ST A mg/d	Resin mg/d	pH	True sp- ecific gravity g/cm ³	CD g/d	TAP g/d	Visco- sity (p)	Rough- ness A	Stren- gth m g
Lower layer Example	12 FeOOH	0		1			0.10	0.019	5.3	120	75	1.15	1.05	9	4.20	1.20	0.54		120	98
	13 FeOOH	0		1			0.30	0.040	7.5	55	100	1.46	1.36	9	3.60	1.40	0.46		140	98
	Comparative Example 5	0		1			0.005	0.003	1.7	320	50	0.66	0.30	9	4.26	1.00	0.66		180	75
	6 FeOOH	0		1			0.60	0.070	8.6	30	110	1.60	1.80	9	3.52	1.60	0.38		230	70
Lower layer Example	14 FeOOH	5		1			0.05	0.011	4.5	190	68	0.80	0.70	9	4.25	1.10	0.54		110	105
	15 FeOOH	5		1			0.10	0.019	5.3	110	75	1.08	0.98	9	4.20	1.16	0.52		110	107
	16 FeOOH	5		1			0.30	0.040	7.5	50	100	1.83	1.73	9	3.60	1.43	0.42		120	106
	Comparative Example 7	5		1			0.60	0.070	8.6	25	110	2.29	2.19	9	3.52	1.60	0.36		200	95
Lower layer Example	17 FeOOH	5	Occluded	1			0.05	0.013	3.8	220	70	0.74	0.64	9	4.23	1.18	0.55		100	107
	18 FeOOH	5		1			0.10	0.023	4.3	120	81	1.01	0.91	9	4.05	1.25	0.5		100	109
	19-A FeOOH	5		0.5			0.30	0.048	6.3	53		1.79	1.78	8				80	125	
	19-B FeOOH	5		1.0			0.30	0.048	6.3	53	103	1.75	1.65	9	3.58	1.45	0.45	30	110	108
	19-C FeOOH	5		2.0			0.30	0.048	6.3	53		1.71	1.48	9.5				10	110	
Comparative Example 8	20 FeOOH	5		1			0.50	0.050	10.0	40	110	1.85	1.75	9	3.55	1.50	0.40		120	100
	FeOOH	5		1			0.60	0.080	7.5	31	112	1.98	1.88	9	3.5	1.6	0.35		180	97

The results arranged in Table 1-A and 1-B show that compared to the comparative examples, the lower base layer formed using α -FeOOH according to the present invention has low surface roughness, giving it excellent surface smoothness adequate strength. Thus, as described in the foregoing, when the non-magnetic lower layer is formed with

α -FeOOH particles according to this invention, using acicular metal particles having the component composition and properties listed below to constitute the upper layer enables a magnetic recording medium having a multi layer structure to be obtained that exhibits excellent magnetic properties, surface qualities, strength and weather resistance.

Next, the magnetic particles used for the upper layer are acicular ferromagnetic metal particles of Fe containing from more than 5 to 50 at.% Co, 0.1 to 30 at.% Al, 0.1 to 10 at.% rare earth elements (including Y), up to 0.05 wt.% periodic table group 1a elements and up to 0.1 wt.% (including 0 wt.%) periodic table group 2a elements. It is preferable that these acicular ferromagnetic metal particles have an average major axis diameter of 0.01 to 0.4 μm , a BET specific surface area of 30 to 70 m^2/g , a crystalline diameter of 50 to 250 angstrom, a coercive force H_c of 1200 to 3000 (Oe) and a saturation magnetic flux density σ_s of 100 to 200 (emu/g). It is also preferable that the acicular ferromagnetic metal particles used do not release more than 2 wt.% H_2O at 100°C and not more than 4.0 wt.% H_2O at 300°C.

To briefly outline the reasons for the stated limits on the content ranges of the constituent components of the metal particles, Co improves the coercive force H_c and saturation magnetic flux density σ_s , helps to reduce crystalline diameter, and is also effective for avoiding a lowering of $\Delta\sigma_s$ shown below in the Examples. However, with a Co content of 5 at.% or less, these effects are not sufficiently realized. On the other hand, the coercive force H_c is decreased if the Co content is more than 50 at. %, so the content range is defined as from more than 5 at.% to not more than 50 at.%. Preferably the Co content is from over 4 to 40 at.%, more preferably 10 to 35 at.%.

Al improves the dispersibility (sintering prevention) of the fine acicular particles, and during reduction of the particles has a pronounced shape-maintaining effect. This effect is not realized with less than 0.1 at.% Al, while more than 30 at.% reduces the saturation magnetization, degrading the magnetic properties. Therefore the Al content range is set at 0.1 to 30 at.%, preferably 1 to 20 at.%, more preferably 5 to 15 at.%. With respect to when the Al is contained as a compound (oxide), the Al content specified refers not to the amount of the compound but to the content of just the element Al.

Like Al, rare earth elements (including Y) prevent sintering of the metal particles, improving dispersibility. With a content of less than 0.1 at.%, the effect is so small that sintering occurs readily, while exceeding 10 at.% increases the amount of oxides of the various elements, reducing the saturation magnetization, which is unsuitable for the magnetic metal particles for the upper layer. Rare earth elements that are usable include Y, La, Ce, Pr, Nd, Sm, Tb, Dy, and Gd. When used in combination the total amount is set at 0.1 to 10 at.%. With respect to when these elements are contained as a compound, the content specified herein refers not to the amount of the compound but to the content amount in the compound of the element concerned.

Periodic table group 1a elements that are usable include Li, Na, and K. If a soluble salt of such elements adheres to the surface of the particles, the dispersibility of the particles in the resinous binder deteriorates and the storage-stability and weather resistance of the product medium are degraded. Thus the content amount of these elements is set at not more than 0.05 wt.%. Even if these elements are used in combination, the total amount is still limited to not more than 0.05 wt.%. These group 1a elements promote sintering during the reduction step of the process used to manufacture the acicular ferromagnetic particles, so prior to the reduction step it is desirable to exclude them as much as possible.

Periodic table group 2a elements that are usable include Mg, Ca, Sr, and Ba. If a soluble salt of such elements adheres to the surface of the particles, the dispersibility of the particles in the resinous binder deteriorates and the storage-stability and weather resistance of the product medium are degraded. The content amount of these elements therefore is set at not more than 0.1 wt. %, including when used in combination.

With respect to moisture held by the metal particles, the amount detected (released) at 100°C should be not more than 2.0 wt.%, preferably not more than 1.5 wt.%, and the amount detected (released) at 300°C should be not more than 4.0 wt.%, preferably not more than 3.0 wt.%. The viscosity of the coating material and the binder adsorption amount both depend on the moisture amount held by the metal particles. If the amount of H_2O detected at 100°C is more than 2.0 wt.%, or if the amount detected at 300°C is more than 4.0 wt.%, dispersal of the coating on the lower layer will be insufficient, making it difficult to form tape.

A suitable size for the acicular metal particles is an average major axis diameter of 0.01 to 0.4 μm , preferably 0.04 to 0.2 μm . Particles with an average major axis diameter that is less than 0.01 μm become superparamagnetic, which sharply reduces the electromagnetic conversion characteristics, while exceeding 0.4 μm results in metal particles having multiple magnetic domains, which reduces the electromagnetic conversion characteristics. Therefore, to ensure the magnetic recording medium having a multilayer structure has the intended magnetic properties, the acicular particles used should have an average major axis diameter of 0.01 to 0.4 μm .

A suitable BET specific surface area for the metal particles is 30 to 70 m^2/g , preferably 40 to 60 m^2/g . A specific surface area that is less than 30 m^2/g result in deterioration of the compatibility with the resin during tape formation, degrading the electromagnetic conversion characteristics, while exceeding 70 m^2/g results in poor dispersion during tape formation, which also degrades the electromagnetic conversion characteristics.

A suitable size for the crystals of the magnetic metal particles is 50 to 250 angstrom, preferably 100 to 200 angstrom. If the crystals are smaller than 50 angstrom the magnetic particles will become superparamagnetic, sharply

reducing the electromagnetic conversion characteristics, while crystals that are larger than 250 angstrom result in higher noise, which also reduces electromagnetic conversion characteristics.

The higher the coercive force H_c of the magnetic metal particles is, the more suitable it is for high-density recording. However, taken together with the performance of the magnetic head, the coercive force is controlled to 1200 to 3000 (Oe), preferably 1600 to 2600 (Oe). The higher the saturation magnetic flux density σ_s is, the higher the output becomes, but to achieve a balance with oxidation resistance, noise and the like, 120 to 180 emu/g is preferable.

Metal particles having the described composition and properties can be produced by adding a prescribed amount of Al to Co-containing α -FeOOH or iron oxide and reducing the result at an elevated temperature. As the particle compound containing α -FeOOH or iron oxide as the main component that is thus subjected to heat-reduction, there can be used α -FeOOH, γ -FeOOH, α -Fe₂O₃, γ -Fe₂O₃, Fe₃O₄, and compounds corresponding to intermediates thereof, and a metal component added thereto such as Ni, Cr, Mn, Zn and the like, with substances having good acicular properties being preferred.

Water-soluble salts such as Al₂(SO₄)₃, Al(NO₃)₃, AlCl₃, and water-soluble aluminates such as NaAlO₂ are usable as the Al compound used to add the Al. These Al compounds may be coated on the surface of the particles by dissolving the Al compound in an alkaline solution, dispersing the particles in the solution and neutralizing the solution by blowing carbonic gas into the solution or by adding an acid, thereby cladding the surface of the particles with Al in the form of crystalline or amorphous Al₂O₃ · nH₂O (aluminum hydroxide). The Al can also be occluded within the particles.

The Al can be occluded in Co-containing α -FeOOH or γ -FeOOH by adding a water-soluble Al salt or aluminate to the reaction system used to produce the α -FeOOH or γ -FeOOH by using a neutralizer such as NaOH, Na₂CO₃, or NH₄OH to neutralize a solution in which the main component is a ferrous salt such as FeSO₄ or FeCl₂, and then oxidizing the solution in air. The Al may also be occluded in Co-containing α -Fe₂O₃ by using a solution of a ferric salt such as Fe₂(SO₄)₃ or FeCl₃, for example, and a neutralizer such as NaOH or KOH and adding the above water-soluble Al salt or aluminate to the reaction system used to synthesize Fe₂O₃ by hydrothermal synthesis.

The Co-containing α -FeOOH or iron oxide with added Al can then be heated to fix the Al as Al₂O₃ to form the material used in the step in which Y (including rare earth elements) is added. At this point, the α -FeOOH is transformed to iron oxide by dehydration. Methods that can be used include dispersing the source particles in a solution containing Y and adding an alkali to effect precipitation in the form of a hydroxide, or dispersing the source particles in a Y compound solution and evaporating the water. Iron oxide particles to which a prescribed amount of Co, Al and Y (including rare earth elements) has been added by the above methods are reduced by being heated in a reducing atmosphere to obtain magnetic metal particles which have reduced iron as the main component and contain Co, Al and Y (including rare earth elements).

In specifying a periodic table group 1a element content of not more than 0.05 wt.% and a periodic table group 2a element content of not more than 0.1 wt.% for the magnetic metal particles, in addition to using source materials that include no group 1a or 2a elements or as little as possible, it is also preferable to remove such elements by thoroughly washing the compounds at each of the FeOOH, iron oxide, and magnetic metal particle stage. Washing becomes increasingly effective, since with the progress from step to step, the above elements migrate to the surface of the particles. The removal effect is enhanced by using hot water or water to which acid has been added to reduce the pH. If the content of group 1a elements exceeds 0.05 wt.%, when it comes to forming the tape, compatibility with the resin deteriorates, preventing dispersion, and even if the magnetic coating material is formed, the coating film has low strength. Moreover, since these elements are soluble, if the tape is kept for a certain time, the elements precipitate on the tape surface, forming crystalline compounds that increase dropouts and degrade the storage stability of the tape. If the content of group 2a elements exceeds 0.1 wt.%, compatibility with the resin and coating film strength are both reduced; if a very high content is used, as in the case of group 1a elements, the storage stability of the tape is degraded.

The substrate used to form the multilayer magnetic recording medium may be a known film of a polyester such as polyethylene terephthalate, polyethylene naphthalate, a polyolefin, cellulose triacetate, polycarbonate, polyamide, polyimide, polyamide-imide, polysulfone aramide, or aromatic polyamide.

Representative examples of the coating type magnetic recording medium having a multilayer structure (a tape) in accordance with this invention will now be described, together with comparative examples.

EXAMPLES

Example 1

A lower layer coating material having the following composition was prepared.

α -FeOOH	100 parts by weight
(In this example, the major axis diameter was 0.15 μ m and moisture amount at 100°C was 1 wt.%.)	
Polyurethane resin	20 parts by weight
Methyl ethyl ketone	165 parts by weight
Cyclohexanon	65 parts by weight
Toluene	165 parts by weight
Stearic acid	1 part by weight
Acetyl acetone	1 part by weight

Coating material having the above composition obtained after dispersion for one hour using a centrifugal ball mill was applied with an applicator to a polyethylene terephthalate base film to form a lower layer. The properties of the α -FeOOH particles used and of the lower layer thus obtained are listed in Table 2-(2) which is continued from Table 2-(1). The measurement methods used were the same used with respect to the test examples of Table 1 (A,B).

An upper layer coating material having the following composition was prepared.

Magnetic metal particles	100 parts by weight
(In this example, Fe containing 30 at.% Co, 10 at.% Al, 4 at.% Y, 0.002 wt.% Na, and 0.004 wt.% Ca)	
Polyurethane resin	30 parts by weight
Methyl ethyl ketone	190 parts by weight
Cyclohexanon	80 parts by weight
Toluene	110 parts by weight
Butyl stearate	1 part by weight
Acetyl acetone	1 part by weight
α -alumina	3 parts by weight
Carbon black	2 parts by weight

Upper layer coating material having the above composition obtained after dispersion for one hour using a centrifugal ball mill was coated on the above lower layer with an applicator to form a sample sheet that was calendered and slit into 8-mm widths to form magnetic tape. The properties of the magnetic metal particles used and of the magnetic tape thus obtained are listed in Table 2-(1) which follows to Table 2-(2).

The following Examples are also listed in Table 2-(1) and Table 2-(2), and the following comparative examples are listed in Table 3-(1) and Table 3-(2).

Example 2

Magnetic tape was obtained in the same way as in Example 1 except that instead of the α -FeOOH particles having a major axis diameter of 0.15 μ m used to form the lower layer in Example 1, α -FeOOH particles were used having a major axis diameter of 0.30 μ m.

Example 3

Magnetic tape was obtained in the same way as in Example 1 except that instead of the Co content, Y content and

major axis diameter of the magnetic metal particles used to form the upper layer in Example 1, magnetic metal particles having a Co content of 10 at.%, Y content of 2 at.% and a major axis diameter of 0.095 μm were used.

Example 4

Magnetic tape was obtained in the same way as in Example 1 except that instead of the $\alpha\text{-FeOOH}$ particles having a major axis diameter of 0.15 μm used to form the lower layer in Example 1, $\alpha\text{-FeOOH}$ particles were used having a major axis diameter of 0.30 μm and 5 wt.% Al cladding.

Example 5

Magnetic tape was obtained in the same way as in Example 1 except that instead of the $\alpha\text{-FeOOH}$ particles having a major axis diameter of 0.15 μm used to form the lower layer in Example 1, $\alpha\text{-FeOOH}$ particles were used having a major axis diameter of 0.30 μm and 5 wt.% occluded Al.

Example 6

Magnetic tape was obtained in the same way as in Example 5 except that instead of the Co content, Al content and Y content and major axis diameter of the magnetic metal particles used to form the upper layer in Example 5, magnetic metal particles having a Co content of 30 at.%, Al content of 8 at.%, Y content of 3 at.% and a major axis diameter of 0.08 μm were used.

Example 7

Magnetic tape was obtained in the same way as in Example 1 except that instead of the $\alpha\text{-FeOOH}$ particles having a major axis diameter of 0.15 μm used to form the lower layer in Example 1, $\alpha\text{-FeOOH}$ particles were used having a major axis diameter of 0.10 μm and 5 wt.% occluded Al.

Example 8

Magnetic tape was obtained in the same way as in Example 5 except that instead of the Y content of the magnetic metal particles used to form the upper layer in Example 5, magnetic metal particles having a La content of 4 at.% were used.

Example 9

Magnetic tape was obtained in the same way as in Example 5 except that instead of the Co content, Al content and Y content and major axis diameter of the magnetic metal particles used to form the upper layer in Example 5, magnetic metal particles having a Co content of 10 at.%, Al content of 10 at.%, Y content of 4 at.% and a major axis diameter of 0.08 μm were used.

Example 10

Magnetic tape was obtained in the same way as in Example 5 except that instead of the Co content, Al content and Y content and major axis diameter of the magnetic metal particles used to form the upper layer in Example 5, magnetic metal particles having a Co content of 20 at.%, Al content of 10 at.%, Y content of 4 at.% and a major axis diameter of 0.08 μm were used.

Example 11

Magnetic tape was obtained in the same way as in Example 5 except that instead of the Co content, Al content and Y content and major axis diameter of the magnetic metal particles used to form the upper layer in Example 5, magnetic metal particles having a Co content of 40 at.%, Al content of 10 at.%, Y content of 4 at.% and a major axis diameter of 0.08 μm were used.

Example 12

Magnetic tape was obtained in the same way as in Example 5 except that instead of the Co content, Al content and

Y content and major axis diameter of the magnetic metal particles used to form the upper layer in Example 5, magnetic metal particles having a Co content of 50 at.%, Al content of 10 at.%, Y content of 4 at.% and a major axis diameter of 0.08 μm were used.

5 Example 13

Magnetic tape was obtained in the same way as in Example 5 except that instead of the Co content, Al content, Y content, Na content, Ca content and major axis diameter of the magnetic metal particles used to form the upper layer in Example 5, magnetic metal particles having a Co content of 30 at.%, Al content of 10 at.%, Y content of 4 at.%, Na content of 0.006 wt.%, Ca content of 0.12 wt.% and a major axis diameter of 0.08 μm were used.

Example 14

15 Magnetic tape was obtained in the same way as in Example 1 except that instead of the α -FeOOH particles used to form the lower layer in Example 1, α -FeOOH particles having a major axis diameter of 0.30 μm and a Si content of 2.5 wt.% were used.

Example 15

20 Magnetic tape was obtained in the same way as in Example 1 except that instead of the α -FeOOH particles used to form the lower layer in Example 1, α -FeOOH particles were used having a major axis diameter of 0.30 μm , 5 wt.% occluded Al and 2.5 wt.% Si.

Comparative example 1

25 Magnetic tape was obtained in substantially the same way as in Example 1 except that instead of the α -FeOOH particles used to form the lower layer in Example 1, α -Fe₂O₃ particles were used having a major axis diameter of 0.15 μm .

30 Comparative example 2

Magnetic tape was obtained in substantially the same way as in Example 1 except that instead of the α -FeOOH particles used to form the lower layer in Example 1, titanium oxide particles were used having an average diameter of 0.035 μm .

35 Comparative example 3

40 Magnetic tape was obtained in the same way as in Example 1 except that instead of the α -FeOOH particles used to form the lower layer in Example 1, α -FeOOH particles were used having a major axis diameter of 0.30 μm and 35 wt.% occluded Al.

Comparative example 4

45 Magnetic tape was obtained in the same way as in Example 5 except that instead of the Co content, Al content, Y content and major axis diameter of the magnetic metal particles used to form the upper layer in Example 5, magnetic metal particles having a Co content of 3 at.%, Al content of 10 at.%, Y content of 4 at.% and a major axis diameter of 0.08 μm were used.

Comparative example 5

50 Magnetic tape was obtained in the same way as in Example 5 except that instead of the Co content, Al content, Y content and major axis diameter of the magnetic metal particles used to form the upper layer in Example 5, magnetic metal particles having a Co content of 55 at.%, Al content of 10 at.%, Y content of 4 at.% and a major axis diameter of 0.08 μm were used.

55 Comparative example 6

Magnetic tape was obtained in the same way as in Example 5 except that instead of the Co content, Al content, Y

content and major axis diameter of the magnetic metal particles used to form the upper layer in Example 5, magnetic metal particles having a Co content of 30 at.%, Al content of 0 at.%, Y content of 4 at.% and a major axis diameter of 0.08 μm were used.

5 Comparative example 7

Magnetic tape was obtained in the same way as in Example 5 except that instead of the Co content, Al content, Y content and major axis diameter of the magnetic metal particles used to form the upper layer in Example 5, magnetic metal particles having a Co content of 30 at.%, Al content of 35 at.%, Y content of 4 at.% and a major axis diameter of 0.08 μm were used.

Comparative example 8

Magnetic tape was obtained in the same way as in Example 5 except that instead of the Co content, Al content, Y content and major axis diameter of the magnetic metal particles used to form the upper layer in Example 5, magnetic metal particles having a Co content of 30 at.%, Al content of 10 at.%, Y content of 0 at.% and a major axis diameter of 0.08 μm were used.

Comparative example 9

Magnetic tape was obtained in the same way as in Example 5 except that instead of the Co content, Al content, Y content and major axis diameter of the magnetic metal particles used to form the upper layer in Example 5, magnetic metal particles having a Co content of 30 at.%, Al content of 10 at.%, Y content of 15 at.% and a major axis diameter of 0.08 μm were used.

Comparative example 10

Magnetic tape was obtained in the same way as in Example 5 except that instead of the Co content, Al content, Y content, Na content, Ca content and major axis diameter of the magnetic metal particles used to form the upper layer in Example 5, magnetic metal particles having a Co content of 30 at.%, Al content of 10 at.%, Y content of 4 at.%, Na content of 0.16 wt.%, Ca content of 0.12 wt.% and a major axis diameter of 0.08 μm were used.

Comparative example 11

Magnetic tape was obtained in the same way as in Example 1 except that instead of the α -FeOOH particles used to form the lower layer in Example 1, particles were used having a major axis diameter of 0.30 μm , 5 wt.% occluded Al and 35 wt.% Si.

Comparative example 12

Magnetic tape was obtained in the same way as in comparative example 11 except that instead of the moisture amount of the magnetic metal particles used to form the upper layer in comparative example 11, particles were used having 3.5 wt.% moisture at 100°C and 5.5 wt.% moisture at 300°C.

Comparative example 13

Magnetic tape was obtained in the same way as in comparative example 11 except that instead of the moisture amount of the magnetic metal particles used to form the lower layer in comparative example 11, the magnetic metal particles were used having 3.5 wt.% moisture at 100 °C.

Table 2 - (1)

Upper layer																			
Example No.	Component Contents of Metal magnetic particles						Moisture content		Particle properties						Magnetic properties				
	Co act	Al act	Y act	La act	Na wt%	Soluble Ca wt%	Moisture content at 100°C wt%	Moisture content at 300°C wt%	Major axis diameter μm	Aspect ratio	BET m ² /g	Crystal size Å	Particle pH	St. adsorption mg/d	H c O e	σ s emu/g	σ r/ σ s	Δ σ s %	
Example																			
	1	30	10	4	0	0.002	0.004	1.0	1.7	0.08	5	49	170	9.4	101	2340	146	0.52	9.2
	2	30	10	4	0	0.002	0.004	1.0	1.7	0.08	5	49	170	9.4	101	2340	146	0.52	9.2
	3	10	10	2	0	0.002	0.004	1.0	1.7	0.095	5	57	175	9.5	115	1820	130	0.51	9.8
	4	30	10	4	0	0.002	0.004	1.0	1.7	0.08	5	49	170	9.4	101	2340	146	0.52	9.2
	5	30	10	4	0	0.002	0.004	1.0	1.7	0.08	5	49	170	9.4	101	2340	146	0.52	9.2
	6	30	8	3	0	0.002	0.004	1.0	1.7	0.08	5	48	160	9.4	98	2300	147	0.52	10.2
	7	30	10	4	0	0.002	0.004	1.0	1.7	0.08	5	49	170	9.4	101	2340	146	0.52	9.2
	8	30	10	0	4	0.002	0.004	1.0	1.7	0.08	5	49	170	9.3	101	2335	146	0.52	9.3
	9	10	10	4	0	0.002	0.004	1.0	1.7	0.08	5	53	185	9.4	111	2040	131	0.51	11.2
	10	20	10	4	0	0.002	0.004	1.0	1.7	0.08	5	51	175	9.4	106	2315	140	0.52	9.3
	11	40	10	4	0	0.002	0.004	1.0	1.7	0.08	5	48	173	9.4	96	2120	155	0.51	9.2
	12	50	10	4	0	0.002	0.004	1.0	1.7	0.08	4	47	175	9.4	93	2000	153	0.49	9.2
	13	30	10	4	0	0.002	0.12	1.0	1.7	0.08	5	50	170	10.3	109	2346	145	0.51	9.5
	14	30	10	4	0	0.002	0.004	1.0	1.7	0.08	5	49	170	9.4	101	2340	146	0.52	9.2
	15	30	10	4	0	0.002	0.004	1.0	1.7	0.08	5	49	170	9.4	101	2340	146	0.52	9.2

continued in Table 2-(2)

Table 2 - (2)

Example No.	Lower layer											Tape properties											
	Component				Particle properties							Tape properties											
Particulate matter- [a]	Al wt %	Form of Al content	S i wt %	Moisture content at 100°C wt %	Major axis diameter μ m	Minor axis diameter μ m	Aspect ratio	BET d/g	Cryt- al size μ m	Partic- le ph	TAP g/d	True specific gravity g/d	C D g/d	Rough- ness μ m	Stren- gth mg	H c O e	B m G	B r/ B m	Δ B m X	Out- put db	C/N db	Precipi- tation after weather test	
Example																							
1	FeOOH	0		0	1.0	0.15	0.022	6.8	101	80	9	0.52	4.08	1.23	133	95	2350	4100	0.84	3.2	+5.2	+5.4	No
2	FeOOH	0		0	1.0	0.3	0.04	7.5	55	100	9	0.46	3.6	1.4	100	106	2360	4120	0.84	3	+5.1	+5.4	No
3	FeOOH	0		0	1.0	0.15	0.022	6.8	101	80	9	0.52	4.08	1.23	130	95	1870	3200	0.85	3.7	+3.2	+3.4	No
4	FeOOH	5	Clad- ing	0	1.0	0.3	0.04	7.5	50	100	9	0.42	3.6	1.43	100	106	2380	4140	0.84	3	+5.4	+5.5	No
5	FeOOH	5		0	1.0	0.3	0.048	6.3	53	103	9	0.45	3.58	1.45	98	108	2390	4150	0.84	2.8	+5.7	+5.9	No
6	FeOOH	5		0	1.0	0.3	0.048	6.3	53	103	9	0.45	3.58	1.45	99	108	2380	4170	0.84	2.8	+5.6	+5.8	No
7	FeOOH	5		0	1.0		0.023	4.3	120	81	9	0.50	4.05	1.25	99	109	2390	4170	0.84	2.8	+5.6	+6.8	No
8	FeOOH	5		0	1.0	0.3	0.048	6.3	53	103	9	0.45	3.58	1.45	100	107	2385	4150	0.84	2.9	+5.6	+5.8	No
9	FeOOH	5		0	1.0	0.3	0.048	6.3	53	103	9	0.45	3.58	1.45	103	103	2130	3800	0.85	3.8	+4.3	+4	No
10	FeOOH	5		0	1.0	0.3	0.048	6.3	53	103	9	0.45	3.58	1.45	99	107	2365	4090	0.85	3.1	5.2	+5.4	No
11	FeOOH	5		0	1.0	0.3	0.048	6.3	53	103	9	0.45	3.58	1.45	99	107	2200	4350	0.83	3.9	+4.7	+4.9	No
12	FeOOH	5		0	1.0	0.3	0.048	6.3	53	103	9	0.45	3.58	1.45	102	104	2050	4300	0.82	3.9	+3.6	+3.5	No
13	FeOOH	5		0	1.0	0.3	0.048	6.3	53	103	9	0.45	3.58	1.45	111	95	2380	3900	0.83	3.2	+5.3	+5.4	No
14	FeOOH	0		2.5	1.0	0.3	0.048	6.3	61	100	9	0.42	3.63	1.44	94	120	2370	4140	0.84	3	+4.2	+4.3	No
15	FeOOH	5	Occlu- ded	2.5	1.0	0.3	0.048	6.3	58	103	9	0.43	3.58	1.47	94	109	2395	4160	0.84	2.8	+5.9	+6.0	No

Table 3 - (1)

Example No.	Upper layer																		
	Component Contents of Metal magnetic particles						Moisture content		Particle properties				Magnetic properties						
Comparative Example	Co	Al	Y	La	Na	Soluble Ca	Moisture content at 100°C	Moisture content at 300°C	Major axis diameter μ m	Aspect ratio	BET surface area m^2/g	Cryt- al size μ	Particle pH	St. adsorption mg/d	H c O e	σ s	σ r / σ s	Δ σ s	
	act	act	act	act	act	wt%	wt%	wt%								emu/g		%	
	1	30	10	4	0	0.002	0.004	1.0	1.7	0.08	5	49	170	9.4	101	2340	146	0.52	9.2
	2	30	10	4	0	0.002	0.004	1.0	1.7	0.08	5	49	170	9.4	101	2340	146	0.52	9.2
	3	30	10	4	0	0.002	0.004	1.0	1.7	0.08	5	49	170	9.4	101	2340	146	0.52	9.2
	4	3	10	4	0	0.002	0.004	1.0	1.7	0.08	6	53	200	9.4	103	1960	121	0.49	14.2
	5	55	10	4	0	0.002	0.004	1.0	1.7	0.08	4	46	177	9.4	91	1700	150	0.47	9.2
	6	30	0	4	0	0.002	0.004	1.0	1.7	0.08	5	49	180	9.4	107	1650	151	0.49	10.0
	7	30	35	4	0	0.002	0.004	1.0	1.7	0.08	5	72	160	9.0	81	2360	125	0.48	9.3
	8	30	10	0	0	0.002	0.004	1.0	1.7	0.08	5	48	175	9.4	105	2080	149	0.50	10.8
	9	30	10	15	0	0.002	0.004	1.0	1.7	0.08	5	71	155	9.4	118	2390	126	0.52	13.2
	10	30	10	4	0	0.16	0.12	1.0	1.7	0.08	5	48	175	10.9	119	2305	147	0.49	15.2
	11	30	10	4	0	0.002	0.004	1.0	1.7	0.08	5	49	170	9.4	101	2340	146	0.52	9.2
12	30	10	4	0	0.002	0.004	3.5	5.5	0.08	5	49	170	9.4	101	2340	146	0.52	9.2	
13	30	10	4	0	0.002	0.004	1.0	1.7	0.08	5	49	170	9.4	101	2340	146	0.52	9.2	

continued in Table 3 - (2)

Table 3-(2)

Example No.		Lower layer										Tape properties										
		Component				Particle properties						Tape properties										
Particle material	Al wet content	Si wet content at 100°C wt%	Moisture content at 100°C wt%	Major axis diameter μm	Minor axis diameter μm	Aspect ratio	BET m^2/g	Crystallite size \AA	Particle size \AA	TAP g/d	True specific gravity g/d	C/D g/d	Roughness \AA	Strength mg	H c O e	B m G	B r/ B m	ΔB_m %	Out-put dB	C/N dB	Precipitation after weather test	
1	Fe_2O_3		0		0.15	0.025	6	55	170	9	0.65	5.07	1.85	152	90	2300	4030	0.83	3.5	+4.6	+4.8	No
2	TiO_2		0		0.035			40		7		4.1		143	80	2320	4050	0.84	3.3	+4.7	+4.9	No
3	FeOOH	35	0	1.0	0.3	0.06	5	310	107	9	0.46	3.38	1.45									Tape can't be formed
4	FeOOH	5	0	1.0	0.3	0.048	6.3	53	103	9	0.45	3.58	1.45	110	96	2010	3600	0.86	6.3	+3.2	+2.2	No
5	FeOOH	5	0	1.0	0.3	0.048	6.3	53	103	9	0.45	3.58	1.45	103	101	1700	4250	0.78	3.9	+0.9	+1.9	No
6	FeOOH	5	0	1.0	0.3	0.048	6.3	53	103	9	0.45	3.58	1.45	108	86	1600	3800	0.75	3	+1.8	+1.7	No
7	FeOOH	5	0	1.0	0.3	0.048	6.3	53	103	9	0.45	3.58	1.45	112	85	2370	2800	0.74	2.9	+1.7	+1.6	No
8	FeOOH	5	0	1.0	0.3	0.048	6.3	53	103	9	0.45	3.58	1.45	103	103	2100	4050	0.79	2.9	+2.5	+2.1	No
9	FeOOH	5	0	1.0	0.3	0.048	6.3	53	103	9	0.45	3.58	1.45	121	84	2400	2850	0.8	2.9	+2.0	+1.8	No
10	FeOOH	5	0	1.0	0.3	0.048	6.3	53	103	9	0.45	3.58	1.45	116	90	2300	3750	0.74	4.2	Unmeasurable		Yes
11	FeOOH	5	35	1.0	0.3	0.048	6.3	181	103	9	0.4	3.75	1.5	169	80	2375	4120	0.83	3	+3.0	+3.1	No
12	FeOOH	5	35	1.0	0.3	0.048	6.3	181	103	9	0.4	3.75	1.5									Tape can't be formed
13	FeOOH	5	35	3.5	0.3	0.048	6.3	181	103	9	0.4	3.75	1.5									Tape can't be formed

From Tables 2 (1,2) and 3 (1,2), it can be seen that the multi layer magnetic recording medium in which $\alpha\text{-FeOOH}$ particles are used for the lower layer in accordance with the present invention has excellent strength, surface roughness, electromagnetic conversion characteristics and weather resistance. The improvement in magnetic properties is

particularly good when Co, Y and Al are present together in the magnetic metal particles, which also results in the enhanced extraction of magnetic properties by the inventive lower layer.

In comparative example 10 in which the magnetic metal particles for the upper layer have high Na and Ca, dispersion is difficult and even when achieved, the tape has decreased durability and storage stability, with surface crystal precipitation being observed after the tape was left in an atmosphere having a relative humidity of 90% and a temperature of 60°C.

According to its broadest aspect the invention relates to a coating type magnetic recording medium having a multilayer structure, formed on a substrate, comprising a magnetic layer of magnetic particles dispersed in a resinous binder, and a non-magnetic layer of non-magnetic particles dispersed in a resinous binder,


Claims

1. A coating type magnetic recording medium having a multi layer structure, formed on a substrate, comprising a magnetic layer of magnetic particles dispersed in a resinous binder, and a non-magnetic layer of non-magnetic particles dispersed in a resinous binder,
 said magnetic particles being composed of acicular ferromagnetic metal particles of Fe containing from more than 5 to 50 at.% Co, 0.1 to 30 at.% Al, 0.1 to 10 at.% rare earth elements (including Y), up to 0.05 wt.% periodic table group 1a elements and up to 0.1 wt.% (including 0 wt.%) periodic table group 2a elements,
 said non-magnetic particles being composed of acicular particles of α -FeOOH having an average major axis diameter of 0.01 to 0.5 μm and releasing not more than 2 wt.% of H_2O at 100°C.
2. A magnetic recording medium according to claim 1, wherein said acicular ferromagnetic metal particles have an average major axis diameter of 0.01 to 0.4 μm .
3. A magnetic recording medium according to claim 1 or 2, wherein said acicular ferromagnetic metal particles have a BET specific surface area of 30 to 70 m^2/g , a crystalline diameter of 50 to 250 angstrom, a coercive force H_c of 1200 to 3000 (Oe) and a saturation magnetic flux density σ_s of 100 to 200 (emu/g).
4. A magnetic recording medium according to claim 1, 2, or 3, wherein said acicular ferromagnetic metal particles are particles that release not more than 2 wt.% H_2O at 100°C and not more than 4.0 wt.% H_2O at 300°C.
5. A magnetic recording medium according to claim 1, wherein said non-magnetic particles are composed of α -FeOOH containing 0.1 to 30 wt.% Al.
6. A magnetic recording medium according to claim 1, wherein said non-magnetic particles are composed of α -FeOOH containing 0.1 to 30 wt.% Si.
7. A magnetic recording medium according to claim 1, wherein said non-magnetic particles are composed of α -FeOOH and have branches inclined in a prescribed two-dimensional direction.
8. A magnetic recording medium according to claim 1, wherein said non-magnetic particles are composed of α -FeOOH having an atmospheric decomposition temperature of 210°C or above.
9. A coating type magnetic recording medium having a multi layer structure, formed on a substrate, comprising a magnetic layer of magnetic particles dispersed in a resinous binder, and a non-magnetic layer of non-magnetic particles dispersed in a resinous binder.

F i g . 1



F i g . 2





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 97 11 4597

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
X	EP 0 602 533 A (KONISHIROKU PHOTO IND) 22 June 1994 * page 2, line 49 - line 58 * * page 3, line 49 - page 4, line 37 * * page 6, line 46 - line 52 *	9	G11B5/704 G11B5/706
A	* claim 1 * ---	1-8	
A	EP 0 582 472 A (TODA KOGYO CORP) 9 February 1994 * page 3, line 20 - line 27 * -----	1-9	
			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
			G11B
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 10 October 1997	Examiner Klocke, S
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ----- & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03.92 (P/MC01)